We claim:

1. A two component developer for use in electrographic printing comprising substantially spherical toner particles and substantially spherical magnetic carrier particles, the toner particles having a radius R_T and the carrier particles having a radius R_C, wherein R_C is between about $1.5R_T$ and about $10R_T$.

2. The developer of claim 1, wherein R_C is between about $2R_T$ and about $5R_T$.

3. A two-component developer for use in electrographic printing comprising substantially spherical toner particles and substantially spherical magnetic carrier particles, the carrier particles having a dielectric constant ϵ_c of at least about 6, the toner particles having a radius R_T and the carrier particles having a radius R_C, wherein R_C is between about $1.5R_T$ and about $10R_T$.

4. The developer of claim 3, wherein R_C is between about $2R_T$ and about $5R_T$.

5. The developer of claim 3, wherein the carrier particles have a dielectric constant ϵ_c greater than about 10.

6. The developer of claim 5, wherein R_C is between about $2R_T$ and about $5R_T$.

7. The developer of claim 3, wherein the carrier particles have a dielectric constant ϵ_c greater than about 100.

8. The developer of claim 7, wherein R_C is between about $2R_T$ to about $5R_T$.

9. The developer of claim 3, wherein the carrier particles have a dielectric constant ϵ_c greater than about 298.

10. The developer of claim 9, wherein R_C is between about $2R_T$ to about $5R_T$.

11. A method for producing electrographic images comprising the steps of:

   (a) providing an electrographic printer comprising an imaging member, a toning shell located adjacent the imaging member and defining an external electric field of image development therebetween, and a two-component developer, comprising substantially spherical toner particles and substantially spherical magnetic carrier particles, the toner particles having a radius R_T and the carrier particles having a radius R_C, wherein R_C is between about $1.5R_T$ and about $10R_T$; and

   (b) causing developer to move through the external electric field, interacting with an electrostatic image carried on the imaging member.

12. The method of claim 11, wherein R_C is between about $2R_T$ and about $5R_T$.

13. The method of claim 11, wherein the carrier particles have a dielectric constant ϵ_c greater than about 10.

14. The method of claim 13, wherein R_C is between about $2R_T$ and about $5R_T$.

15. The method of claim 11, wherein the carrier particles have a dielectric constant ϵ_c greater than about 100.

16. The method of claim 15, wherein R_C is between about $2R_T$ to about $5R_T$.

17. The method of claim 11, wherein the carrier particles have a dielectric constant ϵ_c greater than about 298.

18. The method of claim 17, wherein R_C is between about $2R_T$ to about $5R_T$.

19. The method of claim 11, wherein the external electric field of image development is less than the electric field produced by a uniformly-charged toner particle of charge q and radius R_T.

20. The developer of claim 1, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 6.

21. The developer of claim 1, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 10.

22. The developer of claim 1, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 50.

23. The developer of claim 1, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 100.

24. The developer of claim 1, the toner particles having a size distribution according to the Schulz distribution with z greater than about 20.

25. The developer of claim 1, the toner particles having a size distribution according to the Schulz distribution with z greater than about 30.

26. The developer of claim 1, the toner particles having a size distribution according to the Schulz distribution with z greater than about 50.

27. The developer of claim 1, the toner particles having a size distribution according to the Schulz distribution with z greater than about 100.